

DATA SHEET



PET-G 3D Filament

Material is specifically developed for 3D printing applications where easy processing and high toughness are crucial. The self-bonding ability will improve the strength and the durability of your creations

Material properties:

Description	Method	Typical value
Density	ASTM D792	1.29 g/cm ³
Glass transition temperature	ASTM D3418	80°C
Melting temperature	DSC	180°C
Heat deflection temperature	ISO 75 (0.45MPa)	68°C
Tensile strength at yield	ISO 527	46 MPa

Printing properties:

Hotend temperature	230 -245°C
Heatbed temperature	70 - 90°C
Cooling print object	0 - 30% fan speed
Nozzle diameter	commonly used
Printing environment	open space or inside of box
Bed surface	commonly used (glassbed, PEI, steel etc..)
Bed adhesive	glue stick for easy removal
Drying	6 - 8 hours at 65°C

Type of spool : 1kg

Weight of empty spool : 180g

WORCAM technology s.r.o.

Jistebník 542, 742 82 Jistebník, Česká republika

Společnost je zapsána v obchodním rejstříku Krajského soudu v Ostravě, oddíl C, vložka 77884

www.worcam.cz

+420739954106